

M6

Application:

- De-acidify lakes, rivers and soil
- Poultry feed
- Glass
- Many other uses

Physical properties

Denisty	2.7 g/cm ³
Refractive index %	1.59
PH value (787/9)	9 Max
Loose Bulk denisty	1.4 g/cm ³
Hardness in Mohs*	3
Moisture	0.20%

Chemical Analysis %

CaCO ₃	99.6
CaO	55.64
MgO	0.15
Fe ₂ O ₃	0.001
Al ₂ O ₃	0.001
SiO ₂	0.01-0.03
L.O.I	43.95

Grain Size Specifications

- Over 1.4 mm = 0 %.
- Under 100 μ \leq 8 % .
- Under 250 μ \leq 15 % .
- More than 80 % between 100 μ - 1 mm.

The data in the Technical Data sheet represents average values which are valid and reliable but not legally binding.
MCC will not be liable for any use of data ,or any damages arising from the use of products for purposes not examind
in detail.

MCC-QC 9/19