

M25

Application:

- Matt finish
- Decorative paints
- Sealants
- Protective coating
- Many other uses

Physical properties


Brightness (RY)	97.5±1
Yellow index	2.8 Max
Refractive index %	1.59
Oil absorption (787/5)	17.5gm/100gm
DOP absorption (787/5)	28.5gm/100gm
PH value (787/9)	9 Max
Loose Bulk density	0.73 ±0.05gm/cm3
Hardness in Mohs*	3
Moisture	0.2% Max

Chemical Analysis %

CaCO ₃	99.6
CaO	55.64
MgO	0.15
Fe ₂ O ₃	0.001
Al ₂ O ₃	0.001
SiO ₂	0.01-0.03
L.O.I	43.95

PSD with Malvern

D97	19-21	micron
D50	3.8-4.5	micron
2um	28±2	%



MCC-QC 9/19