

M60

Application:

- Paper.
- Paints
- Inks
- Adhesives
- Many other uses

Physical properties


Brightness (RY)	97.5±1
Yellow index	2.2 Max
Refractive index %	1.59
Oil absorption (787/5)	21.5±0.5gm/100gm
DOP absorption (787/5)	34.5±0.5gm/100gm
PH value (787/9)	9 Max
Loose Bulk denisty	0.46 ±0.05gm/cm3
Hardness in Mohs*	3
Moisture	0.2% max

Chemical Analysis %

CaCO ₃	99.6
CaO	55.64
MgO	0.15
Fe ₂ O ₃	0.001
Al ₂ O ₃	0.001
SiO ₂	0.01-0.03
L.O.I	43.95

PSD with sedigraph

D97	5-6	micron
D50	1.5-1.7	micron
2um	58-62	%



MCC-QC 9/19